

Solventborne

Product name
ACRYDIC 52-473

Description

ACRYDIC 52-473 is a solventborne thermoplastic acrylic resin for 1K lacquer coatings. ACRYDIC 52-473 has excellent NC and CAB compatibility and fast drying properties. It is recommended for automotive refinishing.

Applications

Automotive refinishing.
Metal coatings.
Aerosol paints.

Key features

Compatible with NC and CAB.
Fast drying.
High gloss.
Hardness.
Gasoline resistance.
Weather resistance.

Characteristics

	ACRYDIC 52-473
Appearance	Clear liquid
Solids content, weight %	49.0 - 51.0
Viscosity, Gardner 25°C	N - S
Color, Gardner	1 max.
Acid value on solution, mgKOH/g	1.0 - 3.0
Solvent	Butyl acetate / Toluene

Storage

Store in a cool, dry, well-ventilated place at temperatures below 25°C.

Safe handling note

Refer to SDS for ACRYDIC 52-473.
Please confirm with our sales representative regarding chemical regulatory status of intended countries.

210604

All information on this data sheet is based on DIC Corporation laboratory tests and characteristics shown here are not sales specifications. Procedures and directions for use of DIC Corporation products are recommendations only, with no warranties expressed or implied. The user is solely responsible for determining suitability of DIC Corporation products for the particular application. DIC Corporation recommends consultation with its technical experts and trials before general or production use of any of its products. DIC Corporation products are provided subject to its standard terms and conditions. This data sheet supersedes all previous publications for the products described herein.