

Solventborne

Product name
ACRYDIC A-134-IM

Description

ACRYDIC A-134-IM is a solventborne thermoplastic acrylic resin for 1K lacquer coatings. ACRYDIC A-134-IM has compatibility with either Nitrocellulose (NC) and Cellulose acetate butyrate (CAB) and fast drying properties. It is recommended for automotive refinishing metallic basecoats as well as clear or solid color topcoats.

Applications

Automotive refinishing.
Motorcycle finishes.
Metal coatings.

Key features

Hardness.
Fast drying.
Color retention.
Weather resistance.
High gloss.
Compatibility with Nitrocellulose (NC) and Cellulose acetate butyrate (CAB).

Characteristics

	ACRYDIC A-134-IM
Appearance	Clear liquid
Solids content, weight %	49.0 - 51.0
Viscosity, Gardner 25°C	Z - Z3
Color, Gardner	1 max.
Acid value on solution, mgKOH/g	1.0 - 5.0
Specific gravity, 25°C	0.97 - 0.98
Solvent	Toluene / Butyl acetate

Storage

Store in a cool, dry, and well-ventilated place as mentioned in SDS.

Safe handling note

Refer to SDS for ACRYDIC A-134-IM.
Please confirm with our sales representative regarding chemical regulatory status of intended countries.

210604

All information on this data sheet is based on DIC Corporation laboratory tests and characteristics shown here are not sales specifications. Procedures and directions for use of DIC Corporation products are recommendations only, with no warranties expressed or implied. The user is solely responsible for determining suitability of DIC Corporation products for the particular application. DIC Corporation recommends consultation with its technical experts and trials before general or production use of any of its products. DIC Corporation products are provided subject to its standard terms and conditions. This data sheet supersedes all previous publications for the products described herein.