

**Solventborne**

**Product name**  
**ACRYDIC LA-9508**

**Description**

ACRYDIC LA-9508 is a solventborne thermoplastic acrylic resin for 1K lacquer metal coatings that can be used also in combination with polyisocyanates for 2K polyurethane coatings. ACRYDIC LA-9508 has excellent adhesion to several kinds of metals. It is recommended for direct to metal (DTM) coatings.

**Applications**

1K lacquer enamel finishes.  
Metal coatings primer.  
Direct to metal (DTM) coatings.

**Key features**

Adhesion to metal substrates like zinc galvanized steel, aluminium and alloy.  
High gloss.  
Chemical resistance.  
BTX free.

**Characteristics**

	<b>ACRYDIC LA-9508</b>
<b>Appearance</b>	Clear liquid
<b>Solids content, weight %</b>	51.0 - 53.0
<b>Viscosity, Gardner 25°C</b>	X - Z
<b>Color, Gardner</b>	1 max.
<b>Acid value on solution, mgKOH/g</b>	4.5 - 8.0
<b>OH value on solids, mgKOH/g</b>	Approx. 60
<b>OH content on solids, %</b>	Approx. 1.82
<b>Specific gravity, 25°C</b>	0.95 - 0.97
<b>Solvent</b>	Butyl acetate / n-Butanol

**Storage**

Store in a cool, dry, and well-ventilated place as mentioned in SDS.

**Safe handling note**

Refer to SDS for ACRYDIC LA-9508.  
Please confirm with our sales representative regarding chemical regulatory status of intended countries.

210604

All information on this data sheet is based on DIC Corporation laboratory tests and characteristics shown here are not sales specifications. Procedures and directions for use of DIC Corporation products are recommendations only, with no warranties expressed or implied. The user is solely responsible for determining suitability of DIC Corporation products for the particular application. DIC Corporation recommends consultation with its technical experts and trials before general or production use of any of its products. DIC Corporation products are provided subject to its standard terms and conditions. This data sheet supersedes all previous publications for the products described herein.