

**Solventborne**

**Product name**  
**ACRYDIC ZHL-200**

**Description**

ACRYDIC ZHL-200 is a solventborne thermoplastic acrylic resin for 1K lacquer coatings. ACRYDIC ZHL-200 has excellent adhesion and appearance properties. It is recommended for one-layer coatings or as a primer for home appliances and consumer electronic coatings.

**Applications**

Home appliances.  
Consumer electronics.  
Furniture coatings.  
Inks.

**Key features**

Appearance.  
Water resistance.  
Adhesion.  
Alcohol resistance.

**Characteristics**

	<b>ACRYDIC ZHL-200</b>
<b>Appearance</b>	Clear liquid
<b>Solids content, weight %</b>	44.0 - 46.0
<b>Viscosity, Gardner 25°C</b>	Z2 - (Z5-Z6)
<b>Viscosity, mPa s 25°C</b>	3620 - 12070
<b>Color, Gardner</b>	2 max.
<b>Acid value on solution, mgKOH/g</b>	6.0 - 12.0
<b>Solvent</b>	Toluene

**Storage**

Store in a cool, dry, and well-ventilated place at temperatures below 25°C.

**Safe handling note**

Refer to SDS for ACRYDIC ZHL-200.  
Please confirm with our sales representative regarding chemical regulatory status of intended countries.

210603

All information on this data sheet is based on DIC Corporation laboratory tests and characteristics shown here are not sales specifications. Procedures and directions for use of DIC Corporation products are recommendations only, with no warranties expressed or implied. The user is solely responsible for determining suitability of DIC Corporation products for the particular application. DIC Corporation recommends consultation with its technical experts and trials before general or production use of any of its products. DIC Corporation products are provided subject to its standard terms and conditions. This data sheet supersedes all previous publications for the products described herein.