

**Solventborne**

**Product name**  
**ACRYDIC ZHP-1276**

**Description**

ACRYDIC ZHP-1276 is a solventborne OH functional acrylic resin to use in combination with polyisocyanates for 2K polyurethane coatings. ACRYDIC ZHP-1276 has excellent adhesion to polyamide and glass filled polyamide. It is recommended for these substrate coatings.

**Applications**

Plastic coatings.

**Key features**

Adhesion to plastic substrates, especially polyamide and glass filled polyamide.  
Water resistance.

**Characteristics**

	<b>ACRYDIC ZHP-1276</b>
<b>Appearance</b>	Clear liquid
<b>Solids Content, weight %</b>	49.0 - 51.0
<b>Viscosity, Gardner 25°C</b>	S - W
<b>Color, Gardner</b>	1 max.
<b>Acid value on solution, mgKOH/g</b>	2 max.
<b>OH value on solution, mgKOH/g</b>	13.0 - 19.0
<b>Solvent</b>	Toluene / Methyl isobutyl ketone

**Storage**

Store in a cool, dry, and well-ventilated place at temperatures below 25°C.

**Safe handling note**

Refer to SDS for ACRYDIC ZHP-1276.

Please confirm with our sales representative regarding chemical regulatory status of intended countries.

210603

All information on this data sheet is based on DIC Corporation laboratory tests and characteristics shown here are not sales specifications. Procedures and directions for use of DIC Corporation products are recommendations only, with no warranties expressed or implied. The user is solely responsible for determining suitability of DIC Corporation products for the particular application. DIC Corporation recommends consultation with its technical experts and trials before general or production use of any of its products. DIC Corporation products are provided subject to its standard terms and conditions. This data sheet supersedes all previous publications for the products described herein.