

Solventborne

Product name
ACRYDIC ZHP-1941

Description

ACRYDIC ZHP-1941 is a solventborne OH functional acrylic resin to use in combination with polyisocyanates for 2K polyurethane coatings. ACRYDIC ZHP-1941 has excellent adhesion to plastics and woods substrates and intercoat adhesion. It is recommended for one-layer coatings or as a primer for polyurethane or UV topcoats.

Applications

Wood coatings.
Home appliances.
Consumer electronics.
Automotive interior coatings.

Key features

Appearance.
Adhesion to plastic and wood substrates.
Metallic pigment orientation.
Intercoat adhesion.

Characteristics

	ACRYDIC ZHP-1941
Appearance	Clear liquid
Solids content, weight %	39.0 - 41.0
Viscosity, Gardner 25°C	Z3 - Z6
Color, Gardner	1 max.
Acid value on solution, mgKOH/g	1.5 - 3.5
OH value on solution, mgKOH/g	13.0 - 19.0
Solvent	Butyl acetate / tert-Butanol

Storage

Store in a cool, dry, and well-ventilated place at temperatures below 25°C.

Safe handling note

Refer to SDS for ACRYDIC ZHP-1941.
Please confirm with our sales representative regarding chemical regulatory status of intended countries.

210603

All information on this data sheet is based on DIC Corporation laboratory tests and characteristics shown here are not sales specifications. Procedures and directions for use of DIC Corporation products are recommendations only, with no warranties expressed or implied. The user is solely responsible for determining suitability of DIC Corporation products for the particular application. DIC Corporation recommends consultation with its technical experts and trials before general or production use of any of its products. DIC Corporation products are provided subject to its standard terms and conditions. This data sheet supersedes all previous publications for the products described herein.