

Solventborne

Product name
ACRYDIC 54-172-60

Description

ACRYDIC 54-172-60 is a solventborne OH functional acrylic resin to use in combination with amino resins for stoving enamels. ACRYDIC 54-172-60 has excellent pigment dispersibility and anti-corrosion properties. It is recommended for consumer electronics topcoats.

Applications

Consumer electronics.

Key features

Pigment dispersibility.
Anti-corrosion when formulated with epoxy resins.

Characteristics

	ACRYDIC 54-172-60
Appearance	Clear liquid
Solids content, weight %	59.0 - 61.0
Viscosity, Gardner 25°C	Z2 - Z4
Color, Gardner	1 max.
Acid value on solution, mgKOH/g	4.0 - 6.0
Solvent	Xylene / n-Butanol / Isobutanol / Butyl cellosolve

Storage

Store in a cool, dry, well-ventilated place at temperatures below 25°C.

Safe handling note

Refer to SDS for ACRYDIC 54-172-60.
Please confirm with our sales representative regarding chemical regulatory status of intended countries.

210607

All information on this data sheet is based on DIC Corporation laboratory tests and characteristics shown here are not sales specifications. Procedures and directions for use of DIC Corporation products are recommendations only, with no warranties expressed or implied. The user is solely responsible for determining suitability of DIC Corporation products for the particular application. DIC Corporation recommends consultation with its technical experts and trials before general or production use of any of its products. DIC Corporation products are provided subject to its standard terms and conditions. This data sheet supersedes all previous publications for the products described herein.