

Solventborne

Product name
ACRYDIC A-141

Description

ACRYDIC A-141 is a solventborne acrylic resin to use in combination with metal carboxylate driers for air drying coatings. ACRYDIC A-141 has fast drying properties, high gloss, hardness and gasoline resistance. It is recommended for metal coatings.

Applications

Architectural coatings.
General industrial coatings.

Key features

Fast drying.
High gloss.
Hardness.
Gasoline resistance.
Yellowing resistance.
High apparent thickness.
Self crosslinking.

Characteristics

	ACRYDIC A-141
Appearance	Clear liquid
Solids content, weight %	49.0 - 51.0
Viscosity, Gardner 25°C	V - Z
Color, Gardner	2.0 max.
Acid value on solution, mgKOH/g	1.0 - 3.0
Solvent	Xylene

Storage

Store in a cool, dry, well-ventilated place at temperatures below 25°C.

Safe handling note

Refer to SDS for ACRYDIC A-141.
Please confirm with our sales representative regarding chemical regulatory status of intended countries.

220322

All information on this data sheet is based on DIC Corporation laboratory tests and characteristics shown here are not sales specifications. Procedures and directions for use of DIC Corporation products are recommendations only, with no warranties expressed or implied. The user is solely responsible for determining suitability of DIC Corporation products for the particular application. DIC Corporation recommends consultation with its technical experts and trials before general or production use of any of its products. DIC Corporation products are provided subject to its standard terms and conditions. This data sheet supersedes all previous publications for the products described herein.