

Solventborne

Product name
ACRYDIC AU-7206

Description

ACRYDIC AU-7206 is a solventborne OH functional acrylic resin to use in combination with polyisocyanates for 2K polyurethane coatings. ACRYDIC AU-7206 has excellent adhesion to plastics and electroplated nickel and chromium. It is recommended for consumer electronics coatings.

Applications

Primer for 2K polyurethane coatings.
Consumer electronics.
Plastic coatings.
Metal coatings.
Electroplated nickel and chromium substrates.

Key features

Adhesion to plastic substrates.
Adhesion to metal substrates.
Chemical resistance.
Intercoat adhesion with 2K polyurethane coatings.
BTX free.

Characteristics

	ACRYDIC AU-7206
Appearance	Clear liquid - Slightly turbid liquid
Solids content, weight %	54.0 - 56.0
Viscosity, Gardner 25°C	V - Z1
Color, Gardner	1 max.
Acid value on solution, mgKOH/g	4.0 - 8.0
OH value on solution, mgKOH/g	32.5 - 38.5
Solvent	Butyl acetate / Methyl ethyl ketone / Methoxypropyl acetate

Storage

Store in a cool, dry, well-ventilated place at temperatures below 25°C.

Safe handling note

Refer to SDS for ACRYDIC AU-7206.
Please confirm with our sales representative regarding chemical regulatory status of intended countries.

210607

All information on this data sheet is based on DIC Corporation laboratory tests and characteristics shown here are not sales specifications. Procedures and directions for use of DIC Corporation products are recommendations only, with no warranties expressed or implied. The user is solely responsible for determining suitability of DIC Corporation products for the particular application. DIC Corporation recommends consultation with its technical experts and trials before general or production use of any of its products. DIC Corporation products are provided subject to its standard terms and conditions. This data sheet supersedes all previous publications for the products described herein.