

Solventborne

Product name
ACRYDIC AU-7513

Description

ACRYDIC AU-7513 is a solventborne OH functional acrylic resin to use in combination with polyisocyanate for 2K polyurethane coatings. ACRYDIC AU-7513 has excellent adhesion to plastics, recoatability and pigment dispersibility. It is recommended for plastic motorcycle parts one-layer (1C-1B) metallic and solid color coatings.

Applications

Plastic (ABS) motorcycle parts one-layer (1C-2B) metallic and solid color coatings.
Metal coatings.

Key features

Adhesion to plastics.
Pigment dispersibility.
Recoatability.

Characteristics

	ACRYDIC AU-7513
Appearance	Clear Liquid
Solids Content, weight %	56.0 - 58.0
Viscosity, Gardner 25°C	X - Z2
Color, Gardner	1 max.
Acid Value on solution, mgKOH/g	1.0 - 5.0
OH Value on solids, mgKOH/g	Approx. 56
Specific Gravity, 25°C	0.99-1.01
Solvent	Xylene / Solvesso-100 / Butyl acetate

Storage

Store in a cool, dry, and well-ventilated place as mentioned in SDS.

Safe handling note

Refer to SDS for ACRYDIC AU-7513.
Please confirm with our sales representative regarding chemical regulatory status of intended countries.

210605

All information on this data sheet is based on DIC Corporation laboratory tests and characteristics shown here are not sales specifications. Procedures and directions for use of DIC Corporation products are recommendations only, with no warranties expressed or implied. The user is solely responsible for determining suitability of DIC Corporation products for the particular application. DIC Corporation recommends consultation with its technical experts and trials before general or production use of any of its products. DIC Corporation products are provided subject to its standard terms and conditions. This data sheet supersedes all previous publications for the products described herein.