TECHNICAL DATA SHEET



Solventborne

Product name ACRYDIC SD-44-LV

Description

ACRYDIC SD-44-LV is a solventborne OH functional acrylic resin to use in combination with amino resins for stoving enamels. ACRYDIC SD-44-LV has excellent flexibility and pasteurization and sterilization resistance. It is recommended for exterior can coatings.

Applications

Exterior can coatings. Industrial metal coatings.

Key features

High gloss. Intercoat adhesion between printing ink and white base. Flexibility. Weather resistance. Pasteurization and sterilization resistance.

Characteristics

	ACRYDIC SD-44-LV	
Appearance	Clear liquid	
Solids content, weight %	49.0 - 51.0	
Viscosity, Gardner 25°C	V - X	
Color, Gardner	3 max.	
Acid value on solution, mgKOH/g	2.0 - 5.0	
Solvent	Solvesso-150	

Storage

Store in a cool, dry, and well-ventilated place at temperatures between 15°C - 45°C.

Safe handling note

Refer to SDS for ACRYDIC SD-44-LV. Please confirm with our sales representative regarding chemical regulatory status of intended countries.

210603

All information on this data sheet is based on DIC Corporation laboratory tests and characteristics shown here are not sales specifications. Procedures and directions for use of DIC Corporation products are recommendations only, with no warranties expressed or implied. The user is solely responsible for determining suitability of DIC Corporation products for the particular application. DIC Corporation recommends consultation with its technical experts and trials before general or production use of any of its products. DIC Corporation products are provided subject to its standard terms and conditions. This data sheet supersedes all previous publications for the products described herein.