

**Solventborne**

**Product name**  
**ACRYDIC SLG-41-60**

**Description**

ACRYDIC SLG-41-60 is a solventborne OH functional thermoplastic acrylic resin that can be used as a 1K lacquer or in combination with amino resins for stoving enamels or with polyisocyanates for 2K polyurethane coatings. ACRYDIC SLG-41-60 has excellent adhesion, high gloss and chemical resistance. It is recommended for Direct to metal (DTM) coatings and as primer for metal coatings.

**Applications**

Direct to metal (DTM) coatings.  
Metal coatings primer.

**Key features**

Adhesion to metals like zinc coated metal, alloy, aluminium and stainless steel. substrate.  
High gloss.  
Chemical resistance.  
Compatible with Nitrocellulose (NC).

**Characteristics**

	<b>ACRYDIC SLG-41-60</b>
<b>Appearance</b>	Clear liquid
<b>Solids content, weight %</b>	59.0 - 61.0
<b>Viscosity, Gardner 25°C</b>	Z - Z4
<b>Color, Gardner</b>	1 max.
<b>Acid value on solution, mgKOH/g</b>	2.0 -5.0
<b>OH value on solids, mgKOH/g</b>	Approx. 60
<b>Specific gravity, 25°C</b>	0.98 - 1.00
<b>Solvent</b>	Xylene / n-Butanol

**Storage**

Store in a cool, dry, and well-ventilated place as mentioned in SDS.

**Safe handling note**

Refer to SDS for ACRYDIC SLG-41-60.  
Please confirm with our sales representative regarding chemical regulatory status of intended countries.

210610

All information on this data sheet is based on DIC Corporation laboratory tests and characteristics shown here are not sales specifications. Procedures and directions for use of DIC Corporation products are recommendations only, with no warranties expressed or implied. The user is solely responsible for determining suitability of DIC Corporation products for the particular application. DIC Corporation recommends consultation with its technical experts and trials before general or production use of any of its products. DIC Corporation products are provided subject to its standard terms and conditions. This data sheet supersedes all previous publications for the products described herein.