

Solventborne

Product name
ACRYDIC ZHL-1063

Description

ACRYDIC ZHL-1063 is a solventborne thermoplastic acrylic resin for 1K lacquer coatings. ACRYDIC ZHL-1063 has excellent intercoat adhesion and water resistance. It is recommended for automotive metallic basecoats.

Applications

1K automotive basecoats.

Key features

Adhesion to plastics.
Intercoat adhesion with 2K polyurethane and UV topcoats.
Metallic brilliance.
Pigment dispersibility.

Characteristics

	ACRYDIC ZHL-1063
Appearance	Clear liquid
Solids content, weight %	39.0 - 41.0
Viscosity, Gardner 25°C	Z3 - Z5
Color, Gardner	1 max.
Acid value on solution, mgKOH/g	2 max.
Solvent	Butyl acetate / n-Butanol / Ethyl acetate

Storage

Store in a cool, dry, well-ventilated place at temperatures below 25°C.

Safe handling note

Refer to SDS for ACRYDIC ZHL-1063.
Please confirm with our sales representative regarding chemical regulatory status of intended countries.

210607

All information on this data sheet is based on DIC Corporation laboratory tests and characteristics shown here are not sales specifications. Procedures and directions for use of DIC Corporation products are recommendations only, with no warranties expressed or implied. The user is solely responsible for determining suitability of DIC Corporation products for the particular application. DIC Corporation recommends consultation with its technical experts and trials before general or production use of any of its products. DIC Corporation products are provided subject to its standard terms and conditions. This data sheet supersedes all previous publications for the products described herein.