

Solventborne

Product name
ACRYDIC ZHP-1432-B

Description

ACRYDIC ZHP-1432-B is a solventborne OH functional acrylic resin to use in combination with polyisocyanates for 2K polyurethane coatings. ACRYDIC ZHP-1432-B has excellent pigment dispersibility. It is recommended for packaging film coatings.

Applications

Packaging films.

Key features

Pigment dispersibility.
High gloss.
Workability.
Heat resistance.

Characteristics

	ACRYDIC ZHP-1432-B
Appearance	Clear liquid
Solids content, weight %	49.0 - 51.0
Viscosity, Gardner 25°C	J - T
Color, Gardner	1 max.
Acid value on solution, mgKOH/g	9.5 - 11.5
OH value on solution, mgKOH/g	37 - 43
Solvent	Methyl ethyl ketone

Storage

Store in a cool, dry, well-ventilated place at temperatures below 25°C.

Safe handling note

Refer to SDS for ACRYDIC ZHP-1432-B.
Please confirm with our sales representative regarding chemical regulatory status of intended countries.

210607

All information on this data sheet is based on DIC Corporation laboratory tests and characteristics shown here are not sales specifications. Procedures and directions for use of DIC Corporation products are recommendations only, with no warranties expressed or implied. The user is solely responsible for determining suitability of DIC Corporation products for the particular application. DIC Corporation recommends consultation with its technical experts and trials before general or production use of any of its products. DIC Corporation products are provided subject to its standard terms and conditions. This data sheet supersedes all previous publications for the products described herein.