

TECHNICAL DATA SHEET**Solventborne****High solids****Product name****BURNOCK EQD-1097****Description**

BURNOCK EQD-1097 is a solventborne OH functional saturated polyester resin to use in combination with polyisocyanates for 2K polyurethane coatings. BURNOCK EQD-1097 has high gloss and excellent balance of hardness and flexibility. It is recommended for exterior coatings.

Applications

Aircraft coatings primer.
Exterior coatings.

Key features

High-solids.
Solubility in several organic solvents.
Fast drying.
High gloss.
Hardness and flexibility balance.
Skydrol resistance.
Weather resistance.

Characteristics

	BURNOCK EQD-1097
Appearance	Clear liquid
Solids content, weight %	76.0 - 80.0
Viscosity, Gardner 25°C	V - Z
Color, Gardner	2 max.
Acid value on solution, mgKOH/g	7.0 - 9.0
OH value on solids, mgKOH/g	260 - 320
Solvent	Amyl methyl ketone

Storage

Store in a cool, dry, well-ventilated place at temperatures below 25°C.

Safe handling note

Refer to SDS for BURNOCK EQD-1097.
Please confirm with our sales representative regarding chemical regulatory status of intended countries.

220322

All information on this data sheet is based on DIC Corporation laboratory tests and characteristics shown here are not sales specifications. Procedures and directions for use of DIC Corporation products are recommendations only, with no warranties expressed or implied. The user is solely responsible for determining suitability of DIC Corporation products for the particular application. DIC Corporation recommends consultation with its technical experts and trials before general or production use of any of its products. DIC Corporation products are provided subject to its standard terms and conditions. This data sheet supersedes all previous publications for the products described herein.