

**Solventborne**

**Product name**  
**BURNOCK PH 2890**

**Description**

BURNOCK PH 2890 is a solventborne thermosetting resol type phenolic resin. BURNOCK PH 2890 has excellent flexibility, adhesion, and chemical resistance. It is recommended for interior can-coating applications.

**Applications**

Interior can coatings.  
Drum coatings.

**Key features**

For products according to FDA regulations (§ 175.300).  
Flexibility and adhesion.  
Chemical resistance, even to Sulphur containing compounds.  
Compatible with various epoxy resins (type 4, 7, 9 etc.) and vinyl resins.

**Characteristics**

	<b>BURNOCK PH 2890</b>
<b>Appearance</b>	Clear, yellowish liquid
<b>Solids content, weight %</b>	54.0 - 56.0
<b>Viscosity, mPa s 25°C</b>	2000 - 3500
<b>Color, mg iodine</b>	100 max.
<b>Hot plate cure, sec/150°C</b>	160 - 200
<b>Solvent</b>	Butyl cellosolve

**Storage**

Store in a cool, dry, well-ventilated place at temperatures below 10°C.

**Safe handling note**

Refer to SDS for BURNOCK PH 2890.  
Please confirm with our sales representative regarding chemical regulatory status of intended countries.

210603

All information on this data sheet is based on DIC Corporation laboratory tests and characteristics shown here are not sales specifications. Procedures and directions for use of DIC Corporation products are recommendations only, with no warranties expressed or implied. The user is solely responsible for determining suitability of DIC Corporation products for the particular application. DIC Corporation recommends consultation with its technical experts and trials before general or production use of any of its products. DIC Corporation products are provided subject to its standard terms and conditions. This data sheet supersedes all previous publications for the products described herein.