TECHNICAL DATA SHEET



Solventborne

Product name Idekyd-1030

Description

Idekyd-1030 is a solventborne short oil alkyd resin that can be used with metal carboxylate driers for air drying coatings or in combination with polyisocyanates for 2K polyurethane coatings. Idekyd-1030 has excellent recoatability and fast drying properties. It is recommended for heavy duty primers and automotive refinishing.

Applications

Heavy duty primers. Automotive refinishing.

Key features

Fast drying. Recoatability. Compatible with aromatic hydrocarbons, esters and ketones. Incompatible with aliphatic hydrocarbons.

Characteristics

	Idekyd-1030
Appearance	Clear liquid
Solids content, weight %	53.0 - 57.0
Viscosity, mPa s 25°C	4000 - 6000
Color, Gardner	6 max.
Acid value on solids, mgKOH/g	20 max.
OH value on solids, mgKOH/g	90 - 110
Type of oil	Soybean
Xylene tolerance	Infinite
Mineral turpentine tolerance	None
Solvent	Xylene

Storage

Store in a cool, dry, and well-ventilated place as mentioned in SDS.

Safe handling note

Refer to SDS for Idekyd-1030. Please confirm with our sales representative regarding chemical regulatory status of intended countries.

All information on this data sheet is based on DIC Corporation laboratory tests and characteristics shown here are not sales specifications. Procedures and directions for use of DIC Corporation products are recommendations only, with no warranties expressed or implied. The user is solely responsible for determining suitability of DIC Corporation products for the particular application. DIC Corporation recommends consultation with its technical experts and trials before general or production use of any of its products. DIC Corporation products are provided subject to its standard terms and conditions. This data sheet supersedes all previous publications for the products described herein.