

Solventborne
Product name
Idekyd-1325
Description

Idekyd-1325 is a solventborne acrylic modified alkyd resin that can be used with metal carboxylate driers for air drying coatings or in combination with polyisocyanates for 2K polyurethane coatings. Idekyd-1325 has excellent recoatability and fast drying properties. It is recommended for heavy duty primers, automotive refinishing and aerosol paints.

Applications

Heavy duty primers.
Automotive refinishing.

Key features

High gloss.
Fast drying.
Recoatability.
Compatible with aromatic hydrocarbons, esters and ketones.
Incompatible with aliphatic hydrocarbons.

Characteristics

	Idekyd-1325
Appearance	Clear liquid
Solids content, weight %	58.0 - 62.0
Viscosity, mPa s 25°C	1200 - 1800
Color, Gardner	6 max.
Acid value on solids, mgKOH/g	15 max.
OH value on solids, mgKOH/g	25 - 35
Type of oil	Soybean / DCO
Oil length, %	18
Xylene tolerance	Infinite
Solvent	Xylene

Storage

Store in a cool, dry, and well-ventilated place as mentioned in SDS.

Safe handling note

Refer to SDS for Idekyd-1325.
Please confirm with our sales representative regarding chemical regulatory status of intended countries.

220520

All information on this data sheet is based on DIC Corporation laboratory tests and characteristics shown here are not sales specifications. Procedures and directions for use of DIC Corporation products are recommendations only, with no warranties expressed or implied. The user is solely responsible for determining suitability of DIC Corporation products for the particular application. DIC Corporation recommends consultation with its technical experts and trials before general or production use of any of its products. DIC Corporation products are provided subject to its standard terms and conditions. This data sheet supersedes all previous publications for the products described herein.

DIC Corporation

 For more information: <https://www.dic-global.com/en/products/coating.html>