

**TECHNICAL DATA SHEET****Waterborne****Product name****WATERSOL EFD-5560****Description**

WATERSOL EFD-5560 is a waterborne acrylic modified epoxy ester dispersion to use in combination with metal carboxylates for air drying coatings. WATERSOL EFD-5560 has excellent anti-corrosion and fast drying properties. It is recommended for outdoor architectural coatings.

Applications

Metal coatings.
Automotive and motorcycle coatings.
Architectural exterior coatings.
Protective coatings.

Key features

VOC free.
Fast drying.
Pigment dispersibility.
Impact resistance.
Anti-corrosion.
Storage stability.

Characteristics

	WATERSOL EFD-5560
Appearance	Milky white liquid
Solids content, weight %	39.0 - 41.0
Viscosity, mPa s 25°C	50 - 3000
pH	7.5 - 9.5
Solvent	Water

Storage

Store in a cool, dry, well-ventilated place at temperatures below 25°C.

Safe handling note

Refer to SDS for WATERSOL EFD-5560.

Please confirm with our sales representative regarding chemical regulatory status of intended countries.

210607

All information on this data sheet is based on DIC Corporation laboratory tests and characteristics shown here are not sales specifications. Procedures and directions for use of DIC Corporation products are recommendations only, with no warranties expressed or implied. The user is solely responsible for determining suitability of DIC Corporation products for the particular application. DIC Corporation recommends consultation with its technical experts and trials before general or production use of any of its products. DIC Corporation products are provided subject to its standard terms and conditions. This data sheet supersedes all previous publications for the products described herein.