

Solventborne**Product name**
Idecryl-7043**Description**

Idecryl-7043 is a solventborne OH functional acrylic resin to use in combination with polyisocyanates for 2K polyurethane coatings. Idecryl-7043 has fast drying property. It is recommended for wood coatings topcoat.

Applications

Wood coatings.

Key features

Fast drying.

Characteristics

	Idecryl-7043
Appearance	Clear liquid
Solids content, weight %	48.0 - 52.0
Viscosity, mPa·s 25°C	2400 - 4600
Color, Gardner	1 max.
Acid value on solids, mgKOH/g	6 max.
OH value on solids, mgKOH/g	63 - 69
OH content on solids, %	1.9 - 2.1
Solvent	Butyl acetate

Storage

Store in a cool, dry, and well-ventilated place as mentioned in SDS.

Safe handling note

Refer to SDS for Idecryl-7043

Please confirm with our sales representative regarding chemical regulatory status of intended countries.

240219

All information on this data sheet is based on DIC Corporation laboratory tests and characteristics shown here are not sales specifications. Procedures and directions for use of DIC Corporation products are recommendations only, with no warranties expressed or implied. The user is solely responsible for determining suitability of DIC Corporation products for the particular application. DIC Corporation recommends consultation with its technical experts and trials before general or production use of any of its products. DIC Corporation products are provided subject to its standard terms and conditions. This data sheet supersedes all previous publications for the products described herein.

DIC CorporationFor more information: <https://www.dic-global.com/en/products/coating.html>